Steel threaded pipe fittings

The European Standard EN 10241:2000 has the status of a British Standard $\,$

ICS 23.040.40



National foreword

This British Standard is the official English language version of EN 10241:2000. It supersedes BS 1740-1:1971 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee ISE/19, Ferrous pipe fittings (excluding cast iron), which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the BSI Standards Catalogue under the section entitled "International Standards Correspondence Index", or by using the "Find" facility of the BSI Standards Electronic Catalogue.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 31 and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

This British Standard, having been prepared under the direction of the Engineering Sector Committee, was published under the authority of the Standards Committee and comes into effect on 15 July 2000

ISBN 0 580 34812 1

Amendments issued since publication

| Amd. No. | Date | Comments |
|----------|------|----------|
| | | |
| | | |
| | | |
| | | |

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

EN 10241

April 2000

ICS 23.040.40

English version

Steel threaded pipe fittings

Raccords filetés en acier

Stahlfittings mit Gewinde

This European Standard was approved by CEN on 29 March 2000.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Contents

| Forewo | ord | .3 |
|---|--|----------------|
| 1 | Scope | .4 |
| 2 | Normative references | . 4 |
| 3 | Terms and definitions | .4 |
| 4 | Designation | . 5 |
| 5 5.1 5.2 | Information to be supplied by the purchaser | . 5 |
| 6 6.1 6.2 6.3 6.3.1 | Technical requirements Fitting manufacture Surface condition Material Chemical composition | .6 .6 .6 |
| 6.3.2 6.4 | Mechanical properties Threads | |
| 7 7.1 7.2 7.2.1 7.2.2 7.2.3 | Dimensions and tolerances Dimensions Tolerances Tolerances on length of fitting Tolerances on diameters Tolerance on threads | .7 .7 .7 |
| 8 8.1 8.2 8.2.1 8.2.2 8.2.3 | Protection | 8. 8. 8. |
| 9 9.1 9.1.1 9.1.2 9.2 9.2.1 9.2.2 | Inspection and testing Leaktightness test Hydrostatic test Air test Inspection of thread Inspection method Thread electro zinc plating | .8 .9 .9 |
| 10 | Marking | .9 |
| 11 | Packaging | .9 |
| 12 | Inspection documents | |
| | A (informative) Thread designation and nominal size | |

Foreword

This European Standard has been prepared by Technical Committee ECISS/TC 29, Steel tubes and fittings for steel tubes, the Secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2000, and conflicting national standards shall be withdrawn at the latest by October 2000.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies requirements for threaded fittings of nominal sizes from DN 6 to DN 150 inclusive, made out of welded or seamless steel tubes, forging and rolled bars. It is applicable to those threaded steel pipe fittings that are used in the transportation and distribution of liquid or gas.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporate in it by amendments or revision. For undated references, the latest edition of the publication referred to applies (including amendments).

EN 10204, Metallic products – Types of inspection documents.

EN ISO 6708, Pipework components – Definition and selection of DN (nominal size) (ISO 6708:1995).

ISO 7-1¹⁾, Pipe threads where pressure-tight joints are made on the threads – Part 1: Dimensions, tolerances and designation.

ISO 7-2¹⁾, Pipe threads where pressure-tight joints are made on the threads – Part 2: Verification by means of limit gauges.

ISO 228-1, Pipe threads where pressure-tight joints are not made on the threads – Part 1: Dimensions, tolerances and designation.

ISO 228-2, Pipe threads where pressure-tight joints are not made on the threads – Part 2: Verification by means of limit gauges.

3 Terms and definitions

For the purposes of this standard, the following terms and definitions apply:

3.1

nominal size (DN)

DN: as defined in EN ISO 6708

NOTE The comparison between the thread size designation and the nominal size (DN) is given in Table A.1 for information only.

3.2

seamless fitting

fitting manufactured from seamless tube, forging or rolled bar

3.3

fabricated fitting

fitting manufactured either from a welded tube or where the welding forms part of the fabrication of the fitting

3.4

tubular

fitting manufactured from medium or heavy pipe as defined in Table 6. These fittings are defined in Tables 21 to 24

¹⁾ European Standards are under development (series EN 10226). When published, they may be agreed at the time of enquiry and/or order.

4 Designation

The fitting in accordance with this European Standard shall be designated by the following in the sequence shown:

- type of fitting (see Tables 7 to 24);
- 2) reference to this European Standard (EN 10241);
- 3) either nominal size (DN), or thread size.

Fittings which have the same nominal sizes (DN) are designated only with that DN (see example 1).

EXAMPLE 1:

For an equal female elbow with DN 50 run, the designation will be:

Elbow - EN 10241 - DN 50

Fitting which has differing nominal sizes shall be shown as in the sequence 1-2 where 1 refers to the run and 2 refers to the branch or the reduction (see examples 2 and 3).

EXAMPLE 2:

For a reducing tee with DN 50 run and DN 25 branch, the designation will be:

Reducing tee - EN 10241 - DN 50 × DN 25

EXAMPLE 3:

For a bush with DN 40 and a reduction DN 25, the designation will be:

Bush - EN 10241 - DN 40 × DN 25

5 Information to be supplied by the purchaser

5.1 Mandatory information

The following information shall be supplied by the purchaser, at the time of enquiry and/or order:

- the quantity to be delivered;
- 2) the designation (see clause 4).

5.2 Options

A number of options are specified in this European Standard and they are listed below.

In the event that the purchaser does not indicate a wish to implement any of these options at the time of enquiry and/or order, the fittings shall be supplied in accordance with the basic specification.

- 1) Taper internal thread type Rc conforming to ISO 7-1
- 2) Parallel external thread type GA or GB conforming to ISO 228-1
- 3) Parallel internal thread type G conforming to ISO 228-1
- 4) Zinc protective coating (see 8.2)

Page 6 EN 10241:2000

- 5) Leaktightness test (see 9.1)
- 6) Special packaging (see clause 11)
- 7) Inspection document 2.1 (see clause 12)

6 Technical requirements

6.1 Fitting manufacture

Dimensions and tolerances of differing types of fittings shall be as given in Tables 5 to 24.

6.2 Surface condition

The fitting shall have a smooth surface consistent with the manufacturing process and be free from burrs; surface marks may be ground. Unless otherwise specified in the Tables 11 and 12, the female thread entrance shall be chamfered.

Repairs by welding, other than the weld seam, are forbidden.

6.3 Material

6.3.1 Chemical composition

The fitting shall be manufactured from steel having the chemical composition indicated in Tables 1 and 2.

Table 1 - Chemical composition of seamless steel fittings

| C max. | S max. | P max. |
|--------|--------|--------|
| % | % | % |
| 0,25 | 0,35 | 0,09 |

Table 2 - Chemical composition of fabricated fittings and tubulars

| C max. | Mn max. | P max. | S max. |
|--------|---------|--------|--------|
| | % | % | % |
| 0,25 | 1,40 | 0,045 | 0,045 |

6.3.2 Mechanical properties

The fitting shall be manufactured from base material having the mechanical properties indicated in Tables 3 and 4. These properties shall not be subject to verification on the fitting.

Table 3 - Mechanical properties of seamless steel fittings

| Tensile strength min. | Elongation min. |
|-----------------------|-----------------|
| N/mm² | % |
| 320 | 20 |

Table 4 - Mechanical properties of fabricated fittings and tubulars

| Tensile strength min. | Yieds strength min. | Elongation min. |
|-----------------------|---------------------|-----------------|
| N/mm² | N/mm² | % |
| 320 | 195 | 20 |

6.4 Threads

Internal threads shall be parallel and external threads shall be taper conforming to ISO 7-1, except for certain tubulars in Tables 21, 23 and 24 or when the purchaser specifies other types of thread (see 5.2, option 1 or 2 or 3); in this case the type of thread shall be identified.

7 Dimensions and tolerances

7.1 Dimensions

Fittings shall have the appropriate dimensions given in Tables 6 to 24.

7.2 Tolerances

When tolerances are not specified in Tables 5 to 24, dimensions are nominal and subjected to manufacturing tolerances.

7.2.1 Tolerances on length of fitting

The tolerances on the overall length of the fitting, centre to face, centre to centre and back to face dimensions are given in Table 5.

Table 5 - Tolerances

Dimensions in mm

| Dimension | Up to and including 25 | Over 25 to 40 | Over 40 to 65 | Over 65 to 75 | Over 75 to 150 | Over 150 |
|-----------|------------------------|------------------|------------------|------------------|-------------------|-------------|
| Tolerance | +1,5 0 | +3,0 | +4,5 0 | +6,0 0 | +8,0 | +10,0 |

7.2.2 Tolerances on diameters

Unless otherwise stated in tables, the tolerances on outside diameters are given in Table 6.

7.2.3 Tolerance on threads

The axis of screw threads shall be accurate within $\pm 0.5^{\circ}$ of the specified angle for fittings described in Tables 7 to 23 and $\pm 1.5^{\circ}$ for fittings described in Table 24.

8 Protection

8.1 General

The fitting shall be supplied black and shall be protected by a protective coating, e.g. light oil.

8.2 Zinc protective coating

When a zinc protective coating is specified by the purchaser (see 5.2, option 4), one of the methods given in 8.2.1 to 8.2.3 shall be applied, at the discretion of the manufacturer.

8.2.1 Hot dip zinc galvanizing

Galvanizing of fittings shall be performed before the thread cutting operation and shall be by means of the hot dip method. The minimum average coating thickness shall be 55 μ m on the outside of the fitting, with a local average of 45 μ m on 100 mm².

The hot dip zinc bath shall contain not less than 98,5 % pure zinc.

8.2.2 Electro zinc plating

Electro zinc plating shall be performed on the finished black fitting. The minimum coating thickness on the outside of the fitting shall be 8 μ m.

8.2.3 Zinc flake

Zinc flake non-electrolically applied cured coating shall be performed on the finished black fitting. The coating thickness on the outside of the fitting shall be between 5 μ m to 10 μ m.

NOTE The zinc coating thickness can be checked with an electronic and/or magnetic appliance.

9 Inspection and testing

9.1 Leaktightness test

Each fitting, after being threaded, shall be capable of withstanding, without any signs of leakage, the hydrostatic or air test as specified in clauses 9.1.1 and 9.1.2. This test shall only be carried out when specified by the purchaser at the time of enquiry and/or order (see 5.2, option 5).

9.1.1 Hydrostatic test

Hydrostatic test, using water or light oil as a medium.

9.1.1.1 Tubulars

These shall be tested to a minimum internal pressure of 50 bar.

9.1.1.2 Fabricated fittings

These shall be tested to a minimum internal pressure of 75 bar.

9.1.1.3 Seamless fittings

These shall be tested to a minimum internal pressure of 150 bar.

9.1.2 Air test

Air test, with the fitting fully immersed in water or light oil as a medium.

Tubulars, fabricated fittings and seamless fittings shall be tested to a minimum internal air pressure of 7 bar.

9.2 Inspection of threads

9.2.1 Inspection method

Threads manufactured in accordance with ISO 7-1 shall be verified in accordance with ISO 7-2.

Threads manufactured in accordance with ISO 228-1 shall be verified in accordance with ISO 228-2.

9.2.2 Thread electro zinc plating

Where fittings have been electro zinc plating, this can result in the thread being covered in uneven particles of zinc; these particles may be removed with a plug or a brush.

10 Marking

The manufacturer's brand or logo shall, depending on the size of fittings, either be applied on a label attached on the packaging or be marked indelibly on each fitting.

11 Packaging


Unless special packaging is specified by the purchaser at the time of enquiry and/or order (see 5.2, option 6), fittings shall be supplied, either singly or in sacks or bags.

12 Inspection documents

Fittings shall be delivered without an inspection document.

At the request of purchaser (see 5.2, option 7), the manufacturer shall provide a certificate of compliance, in accordance with EN 10204 type 2.1.

Table 6 - Threaded ends of fitting



1 Taper is 1 in 16 on diameter.

| Taper to this to or diameter. | | | | | | | |
|-------------------------------|-----------------------------|---|-------|--|----------------|-----------------|--|
| Nominal size | Minimum outside diameter | Outside diameter of body behind external thread | | Maximum inside diameter of body behind internal thread | Pipe thickness | | |
| DN | D ¹⁾ | E | -2) | <i>a</i> ³⁾ | T | T ⁴⁾ | |
| | mm | m | ım | mm | mm | | |
| | | min. | max. | | Medium | Heavy | |
| 6 | 15,0 | 9,8 | 10,6 | 8,6 | 2,0 | 2,6 | |
| 8 | 18,5 | 13,2 | 14,0 | 11,4 | 2,3 | 2,9 | |
| 10 | 22,0 | 16,7 | 17,5 | 15,0 | 2,3 | 2,9 | |
| 15 | 27,0 | 21,0 | 21,8 | 18,6 | 2,6 | 3,2 | |
| 20 | 32,5 | 26,5 | 27,3 | 24,1 | 2,6 | 3,2 | |
| 25 | 39,5 | 33,3 | 34,2 | 30,3 | 3,2 | 4,0 | |
| 32 | 49,0 | 42,0 | 42,9 | 39,0 | 3,2 | 4,0 | |
| 40 | 56,0 | 47,9 | 48,8 | 44,8 | 3,2 | 4,0 | |
| 50 | 68,0 | 59,7 | 60,8 | 56,5 | 3,6 | 4,5 | |
| 65 | 84,0 | 75,3 | 76,6 | 72,2 | 3,6 | 4,5 | |
| 80 | 98,0 | 88,0 | 89,5 | 84,9 | 4,0 | 5,0 | |
| 100 | 124,0 | 113,1 | 115,0 | 110,1 | 4,5 | 5,4 | |
| 125 | 151,0 | 138,5 | 140,8 | 135,5 | 5,0 | 5,4 | |
| 150 | 178,0 | 163,9 | 166,5 | 160,9 | 5,0 | 5,4 | |

- 1) The outside diameter *D* is a minimum for all fittings except equal sizes of socket and half socket. The minimum outside diameters of equal sizes of socket and half socket are given in Tables 11 and 12.
- 2) E are minimum and maximum diameters for tubulars in Tables 21 to 24; for other fittings, only the minimum is applicable.
- 3) The value d is not applicable to bushes described in Table 15.
- 4) Wall thickness tolerances for tubulars shall be:
 - no limit in plus;
 - 12,5 % minus.

Table 7 - Elbow, tee and cross, equal




Table 8 - Elbow, equal 45 degrees




Table 9 - Elbow, male and female, equal




Table 10 - Tee, reducing on the branch






Table 11 - Socket and half socket, equal, type heavy



1 Faced at right angle to axis of thread. No internal chamfer.

| Nominal size | Minimum outside diameter | Overall length of socket | Overall length of half socket |
|--------------|--------------------------|--------------------------|-------------------------------|
| DN | А | В | С |
| | mm | mm | mm |
| 6 | 15,0 | 19 | 8 |
| 8 | 18,5 | 27 | 11 |
| 10 | 22,0 | 28 | 12 |
| 15 | 27,0 | 37 | 16 |
| 20 | 32,5 | 39 | 19 |
| 25 | 39,5 | 46 | 21 |
| 32 | 49,0 | 51 | 25 |
| 40 | 56,0 | 51 | 25 |
| 50 | 68,0 | 60 | 28 |
| 65 | 84,0 | 69 | 30 |
| 80 | 98,0 | 75 | 35 |
| 100 | 124,0 | 87 | 40 |
| 125 | 151,0 | 96 | 44 |
| 150 | 177,0 | 96 | 44 |

Table 12 - Socket and half socket, equal, type medium



1 Faced at right angle to axis of thread. No internal chamfer.

| Nominal size | Minimum outside diameter of socket | Overall length of socket | | |
|--------------|------------------------------------|--------------------------|-------|----|
| DN | А | В | С | D |
| | mm | mm | mm | mm |
| 6 | 15,0 | 17 | 15,0 | 8 |
| 8 | 18,5 | 25 | 18,5 | 11 |
| 10 | 21,3 | 26 | 21,3 | 12 |
| 15 | 26,6 | 34 | 26,6 | 15 |
| 20 | 31,8 | 36 | 31,8 | 17 |
| 25 | 39,5 | 43 | 39,5 | 20 |
| 32 | 48,3 | 48 | 48,3 | 22 |
| 40 | 54,5 | 48 | 54,5 | 22 |
| 50 | 66,2 | 56 | 68,0 | 26 |
| 65 | 82,0 | 65 | 84,2 | 30 |
| 80 | 95,0 | 71 | 98,4 | 34 |
| 100 | 121,4 | 83 | 124,0 | 40 |
| 125 | 146,3 | 92 | 149,0 | 44 |
| 150 | 173,3 | 92 | 177,0 | 44 |

Table 13 - Reducing socket¹⁾




Table 14 - Hexagonal nipple, equal





Table 15 - Hexagon bush



1 Thread length in accordance with ISO 7-1.

| Nominal size | Minimum length of external thread for basic gauge length plus die clearance | Thickness of hexagon | Overall length | Width across flats of hexagon |
|------------------|--|----------------------|----------------|-------------------------------|
| DN ¹⁾ | L | Т | Α | В |
| | mm | mm | mm | mm |
| 8 | 12,5 | 6 | 18,5 | 14,0 |
| 10 | 12,5 | 8 | 20,5 | 17,0 |
| 15 | 17,5 | 8 | 25,5 | 22,0 |
| 20 | 19,0 | 10 | 29,0 | 27,0 |
| 25 | 21,0 | 10 | 31,0 | 36,0 |
| 32 | 24,0 | 11 | 35,0 | 46,0 |
| 40 | 24,0 | 13 | 37,0 | 50,0 |
| 50 | 27,0 | 14 | 41,0 | 65,0 |
| 65 | 32,0 | 16 | 48,0 | 78,0 |
| 80 | 35,0 | 19 | 54,0 | 90,0 |
| 100 | 40,0 | 22 | 62,0 | 115,0 |
| 125 | 45,0 | 25 | 70,0 | 140,0 |
| 150 | 45,0 | 25 | 70,0 | 166,0 |

¹⁾ Nominal sizes refer to the size of male end, i.e. the larger diameter of the bush. The smaller diameter of the bush is stated by the purchaser.

NOTE Two types of bush are illustrated, either of which can be supplied.


80

100

125

150

Table 16 - Square head plug



NOTE Plugs may be provided with a shallow concave recess in the base, so long as the essential solidity of the plug is maintained.

37

46

51

60

29,8

35,8

40,1

40,1

22

25

29

32

Table 17 - Hexagon head plug






Table 18 - Socket union



CAUTION A socket union should only be used as complete assembly, because component parts of the union made by different manufacturers, or component parts of different types of union made by the same manufacturer, are not necessarily interchangeable.

NOTE Other external forms of nut and ends are permissible provided that the dimensions in tables are maintained.

Table 19 - Hexagon backnut



¹⁾ The tolerance on width across the flat (W) is ± 0.8 mm.

Table 20 - Cap




Table 21 - Longscrew




Table 21 (continued)

| Nominal size | Minimum useful length of the long thread | Overall length | | | | |
|-----------------|--|---|---|-------------------|-------------------|--|
| DN | В | | A | 4 | | |
| | mm | | m | ım | | |
| 8 | 37 | 100 | 150 | 200 | 250 | |
| 10 | 40 | 100 ¹⁾ | 150 | 200 | 250 | |
| 15 | 52 | 100 ¹⁾ | 150 | 200 | 250 | |
| 20 | 54 | 100 ¹⁾ | 150 | 200 | 250 | |
| 25 | 62 | 100 ¹⁾ | 150 | 200 | 250 | |
| 32 | 70 | 150 ¹⁾ | 200 | 250 | 300 | |
| 40 | 71 | 150 ¹⁾ | 200 | 250 | 300 | |
| 50 | 82 | 150 ¹⁾ | 200 ¹⁾ | 250 | 300 | |
| 65 80 100 | 97 106 121 | 150 ¹⁾ 200 ¹⁾ 200 ¹⁾ | 250 ¹⁾ 250 ¹⁾ 250 ¹⁾ | 250 300 300 | 300 400 400 | |
| 125 | 130 | 250 ¹⁾ | 300 ¹⁾ | 400 | 500 | |
| 150 | 132 | 250 ¹⁾ | 300 ¹⁾ | 400 | 500 | |

¹⁾ Double longscrews cannot be supplied in these lengths.

CAUTION Longscrews should only be used as complete assemblies because component parts of longscrews made by the same or different manufacturers, are not necessarily interchangeable.

NOTE 1 The longscrew parallel thread shall to be of such size, that the socket and backnut shall run on the longscrew, hand-tight, without perceptible shake.

NOTE 2 The socket on the longscrew shall abut the 5 degree angle of the backnut.

NOTE 3 Longscrews shall be made only from heavy tube.

Table 22 - Pipe nipple




Table 23 - Running nipple, close nipple and barrel nipple




Table 24 - Bend and spring




Table 24 (continued)

| | Bend | | | Spring | | | Return bend | |
|-----------------|----------------|-----|--------|----------------|------|---------------------|--------------|-----|
| Nominal Size | 90° | | | Centre to face | | | 180° | |
| | Centre to face | | Radius | A mm | | Centre to centre | Back to face | |
| DN | Α | В | R | 112,5° | 135° | 157,5° | С | D |
| | mm | mm | mm | | | | mm | mm |
| 8 | 64 | 92 | 41 | 60 | 57 | 54 | 51 | 64 |
| 10 | 73 | 105 | 48 | 67 | 64 | 60 | 64 | 70 |
| 15 | 86 | 127 | 57 | 79 | 76 | 73 | 89 | 102 |
| 20 | 102 | 143 | 73 | 92 | 89 | 86 | 102 | 121 |
| 25 | 121 | 168 | 89 | 108 | 105 | 102 | 114 | 140 |
| 32 | 146 | 197 | 108 | 133 | 127 | 124 | 127 | 152 |
| 40 | 165 | 219 | 127 | 149 | 143 | 140 | 165 | 178 |
| 50 | 203 | 264 | 159 | 181 | 175 | 168 | 190 | 210 |
| 65 | 248 | 321 | 197 | 222 | 213 | 206 | 305 | 292 |
| 80 | 292 | 371 | 232 | 260 | 248 | 241 | 356 | 330 |
| 100 | 381 | 467 | 308 | 340 | 324 | 318 | 457 | 400 |
| 125 | 540 | 632 | 380 | 476 | 457 | 444 | 762 | 578 |
| 150 | 622 | 718 | 440 | 572 | 540 | 527 | 914 | 692 |

- NOTE 1 Type 1A bend shall only be made from heavy tube (see Table 6) and fitted with socket and backnut.
- NOTE 2 The angular tolerance shall be as defined in 7.2.3.
- NOTE 3 All threads are taper except where shown above.
- NOTE 4 The end of type 1A bend with paralled thread shall be manufactured in accordance with notes 1 and 2 of Table 21.

Annex A (informative)

Thread designation and nominal size

Table A.1 - Thread designation and nominal size

| Nominal size DN | Designation of thread size/fitting size | | |
|------------------|---|--|--|
| 6 | 1/8 | | |
| 8 | 1/4 | | |
| 10 | 3/8 | | |
| 15 | 1/2 | | |
| 20 | 3/4 | | |
| 25 | 1 | | |
| 32 | 11/4 | | |
| 40 | 11/2 | | |
| 50 | 2 | | |
| 65 | 2 1/2 | | |
| 80 | 3 | | |
| 100 | 4 | | |
| 125 | 5 | | |
| 150 | 6 | | |

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: 020 8996 7002. Fax: 020 8996 7001.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager. Tel: 020 8996 7070.

BSI 389 Chiswick High Road London W4 4AL